

GEOTEXTILE FOR PAVEMENT STABILIZATION:

(2-16-10)

Description

Furnish and install geotextile for pavement stabilization in accordance with the contract. Geotextile for pavement stabilization may be required to prevent longitudinal pavement cracks and provide separation between the subgrade and pavement structure at locations shown on the plans.

Materials

Provide Type 1 Certified Mill Test Report in accordance with Article 106-3 of the *Standard Specifications* and minimum average roll values (MARV) as defined by ASTM D4439 for geotextile properties. For testing geotextiles, a lot is defined as a single day's production.

Load, transport, unload and store geotextiles such that they are kept clean and free of damage. Identify, store and handle geotextiles in accordance with ASTM D4873. Geotextiles with defects, flaws, deterioration or damage will be rejected. Do not leave geotextiles uncovered for more than 7 days.

Use geotextiles with a minimum roll width of 13 ft (4 m) that meet the requirements of Article 1056-1 of the *Standard Specifications*. Machine direction (MD) and cross-machine direction (CD) are as defined by ASTM D4439. Use woven polyester or polypropylene geotextiles with properties meeting the following requirements.

Property	Test Method	Requirement (MARV)	
		MD	CD
Wide Width Tensile Strength @ 5% Strain	ASTM D4595	1900 lbs/ft (27.7 kN/m) min	1900 lbs/ft (27.7 kN/m) min
Wide Width Tensile Strength @ Ultimate	ASTM D4595	4800 lbs/ft (70.0 kN/m) min	4800 lbs/ft (70.0 kN/m) min
Permittivity	ASTM D4491	0.10 sec ⁻¹ min	
Apparent Opening Size	ASTM D4751	30 US sieve (0.60 mm) max	
Ultraviolet Stability (retained strength)	ASTM D4355	70 %* min	
Melting Point	ASTM D276	300 °F (150 °C) min	

*after 500 hours of exposure

Construction Methods

Construct embankments to subgrade elevation in accordance with the Contract. The Engineer will determine if a geotextile for pavement stabilization is required at locations shown on the plans based on testing subgrade soils for quality. For subgrades that are not stabilized, allow 24 calendar days for the Engineer to determine if a geotextile for pavement stabilization is required.